

na.arauco.com

For Cabinets, Furniture, Fixture and INDUSTRIAL APPLICATIONS

ULTRA Custom particleboard is a value engineered particleboard product suitable for a variety of applications including cabinets, furniture, fixtures and general industrial applications.

ULTRA PB CUSTOM				
Bennettsville, SC				
Thickness Range	(in.) (mm)	9 mm - 15 mm	5/8" - 3/4"	13/16" - 1-3/8"
Average MOR	(psi)	1,400	1,400	1,400
Average MOE	(psi)	265,000	265,000	265,000
Average Internal Bond	(psi)	60	60	50
Face Screw Hold	(lb)	180	180	180
Edge Screw Hold*	(Ib.)	-	155	155
Thickness Tolerance	(in.)	+/- 0.005"	+/- 0.005"	+/- 0.005"
Length and Width	(in.)	+/- 1/16"	+/- 1/16"	+/- 1/16"
Squareness	(in.)	1/8"	1/8"	1/8"

- The above physical properties are based on minimum allowable averages of individual production lots. Testing for conformance to the above specifications must be done in accordance with procedures described in the American National Standard for Particleboard. (ANSI 208.1 - 2022 section 6.2 Sampling for Acceptance).
- EPA recognized and CARB approved Third Party Certifier TPC-1.
- EPA TSCA Title VI certified. Complies with CARB ATCM 93120, ANSI 208.1 - 2022, for formaldehyde emissions.
- All panels are approved for interior, non-structural application.
- Contains 100% Recycled/Recovered wood content.

Storage and Handling

Particleboard products should never be stored or used outdoors. The indoor storage area should be clean, dry, well ventilated, and free of dust, dirt or particles that could contaminate the particleboard. Store flat on stickers on a level, hard, dry surface. Constant relative humidity and temperature should be maintained. Before use, allow to stabilize to the same conditions as are expected after the panel is installed. Condition 48 to 72 hours prior to lamination. For more information, see Composite Panels Association Technical Bulletin: Storage and Handling of Particleboard and MDF.

Safety Data Sheets available online.

Note: 'Edge Screw test is not performed on products less than 5/8" thick (per the ANSI standard).





